

Technical Data Sheet ISSUED SEPTEMBER 2020

PRODUCT DESCRIPTION

WPA 560 Moisture Seal is a two component, water-based epoxy, designed as a water and vapour proof coating under water proofing membranes, ceramic tile adhesives*, levelling compounds* and timber floors.

*Note: additional priming required.

Recommended for:

- Primer for damp surfaces;
- Moisture barrier on damp wall/floors;
- Sealing concrete slabs before vinyl and timber overlays;
- Primer for acrylic and polyurethane membranes;
- Dust sealing for interior concrete floors;
- Primer for scyon sheeting;
- Retaining walls;
- Planter boxes;
- Lift Wells;
- Concrete tanks;
- Basements;
- Reservoirs;
- Underground car parks.

FEATURES AND BENEFITS

- Australian made
- Convenient mixing ratio, 1:1 by volume
- Withstands hydrostatic head of water pressure up to 25 meters or 250kPa
- Complies with AS 4020:2005 "Products for use in contact with drinking water"
- Complies with ASTM E96 for water vapour transmission
- Excellent adhesion to building substrates including concrete, fibre cement, all masonry surfaces and Scyon sheeting
- Water-based and user friendly

APPLICATION PROCEDURE

Safety Precautions

Avoid contact with skin and eyes – always wear protective clothing, safety glasses and impervious gloves. Available information suggests that gloves made from nitrile rubber should be suitable for intermittent contact.

Substrates

Suitable for:

- Properly prepared in situ, precast and tilt up concrete;
- Block work;
- Compressed fibre cement sheeting, plasterboard, James Hardie™ Scyon™ Secura™ sheeting.

Surface Preparation

All surfaces to be coated must be firm, clean, dry, sound and smooth. All laitance, grease, oil, wax, curing compounds, loose material, paint and any other contaminants which may reduce or prevent adhesion must be mechanically removed. Masonry surfaces must be pointed flush and surface defects repaired.

Fibre cement sheeting and water resistant plasterboard must be installed in accordance with the manufacturers' installation requirements.

Mixing

WPA 560 Moisture Seal should be mixed with an electric mixer with a high shear mixing paddle. Premix each individual component then join the two components, mixing thoroughly for a no less than 5 minutes until a blended, homogenous liquid is obtained. Avoid trapping air during mixing as this may cause pin holing. Only mix as much product as can be used within the pot life of the product.

Application

WPA 560 Moisture Seal is a minimum two coat system. The coverage rate as specified must be achieved to ensure water transmission barrier and low permeability is obtained.

Apply with a brush, roller ensuring the material is worked into the substrate surface to eliminate pin holing. Successive coats must be applied at right angles to the previous coat.

Each coat must be a minimum of 200 microns wet film thickness to achieve the required dry film thickness of 100 microns per coat. Test the depth of coats with a wet film thickness gauge at regular intervals.

Important: Additional priming is required prior to application of levelling compounds or installation of tiles. Contact the Bayset Technical Department for specific information.

Performance Data and Physical Properties @23°C & 55% RH

- Colour (Mixed): Light grey
- Pot life: 1 hour
- Mix ratio: Pigmented -1:1- A:B by volume
- Re-coat: 4-5 hours
- Full cure: 5-7 days
- Coverage: 4-5m²/litre/coat
- Solids content: 55% by volume
- Storage: Above 5°C

LIMITATIONS

- WPA 560 Moisture Seal cure rates will be affected by surface and ambient temperature and high relative humidity.
- Do not apply to steel or metal surfaces as corrosion may occur.

Technical Data Sheet ISSUED SEPTEMBER 2020

- WPA 560 Moisture seal is a vapour barrier and not a flexible waterproof membrane. A dedicated flexible membrane from the WPA range should be used if a waterproof membrane in conjunction with a vapour barrier is required.
- In enclosed areas, such as water tanks or reservoirs, ventilation should be provided to enable adequate curing.
- Allow to cure for a minimum of 24 hours at 25°C/50% R.H. before applying adhesives, mortars, decorative coatings or other surface treatments.
- WPA 560 Moisture Seal will tend to yellow when left exposed to UV light.
- Discard any material that has exceeded the pot life or working time of the product.
- Do not apply over any substrates that have been previously treated or coated with curing compounds, PVA concrete bonding agents or acrylic coatings. These areas must be mechanically cleaned by grinding or shot blasting to produce a contamination free surface.
- Do not apply if rain is imminent.
- Do not expose to running water or full immersion until fully cured.

Clean Up

Wash all equipment in water with soap or detergent immediately on completion. WPA 560 will cure under water. Do not leave items soaking.

Packaging

8 Litre kit (4 Litre Part A, 4 Litre Part B).

20 Litre kit (10 Litre Part A, 10 Litre Part B).

Shelf Life

12 months in unopened container stored above 5°C.

Precautions

Refer to WPA 560 Moisture Seal MSDS prior to use. WPA 560 Moisture Seal cure rates will be dramatically slowed if the relative humidity is above 85%. Do not add cementitious products to WPA 560 Moisture Seal.

In enclosed areas, such as water tanks, or cubicles, ventilation should be provided to enable adequate evaporation of the coating. Allow to cure for a minimum of 24 hours at 25°C/50% RH before applying waterproofing membranes, adhesives, mortars, decorative coatings or other surface treatments.

Discard any material that has exceeded the pot life or working time of the product. Do not apply over any substrates that have been previously treated or coated with curing compounds, PVA concrete bonding agents or acrylic coatings. These areas must be mechanically cleaned by grinding or shot blasting to produce a contamination free surface.

WPA 560 Moisture Seal is rigid when cured and will not absorb movement cracks.

Subsequent coatings must be applied within 48 hours of the application of WPA 560 Moisture Seal.

Cold Substrates and Cool Climatic Conditions

Follow mixing instructions and allow an extra minute to ensure a homogeneous paste is obtained. Allow to stand for 5 minutes after mixing as this will accelerate the curing time. Never apply thin coats as the rapid moisture loss will arrest or slow the drying reaction which can cause an amine blush. Cure rates will be dramatically slowed if substrate surface or ambient temperature is below +10°C. If WPA 560 Moisture Seal is applied in cooler climatic conditions, low substrate temperatures can produce amine blush, resulting in an oily residue and or areas of uncured tacky discolorations. Remove amine blush and uncured product prior to application of any further coating to ensure adhesion of the next coat. Before recoating, WPA 560 Moisture Seal should be allowed to cure and then washed with clean, fresh water.

24 hours prior to use, store WPA 560 Moisture Seal in a 20°C environment. If possible warm substrate surface area by an air blower or use a blower after application. Always provide adequate ventilation during the drying cycle.

FIRST AID

If poisoning occurs, contact a doctor or Poisons Information Centre (Phone Australia 131 126).

Eye Contact

If this product comes in contact with the eyes:

- Wash out immediately with fresh running water.
- Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids.
- Seek medical attention without delay; if pain persists or recurs seek medical attention.
- Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.

Skin Contact

If skin contact occurs:

- Immediately remove all contaminated clothing, including footwear.
- Flush skin and hair with running water (and soap if available).
- Seek medical attention in event of irritation.

Inhalation

If fumes, aerosols or combustion products are inhaled remove from contaminated area.

Other measures are usually unnecessary.

Technical Data Sheet ISSUED SEPTEMBER 2020

Ingestion

Immediately give a glass of water.

First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.

WARRANTY CONDITIONS

Bayset Pty Ltd trading as Waterproofing Products Australia (Bayset) offers a limited warranty in respect of this product, subject to certain terms and conditions set out in the warranty documentation which has been made available at www.bayset.com.au. Please contact Bayset directly to obtain a copy of the warranty documentation relevant to this product.

DISCLAIMER

The technical information and application advice given in this Technical Data Sheet is based on the present state of Bayset Pty Ltd's best scientific and practical knowledge and is intended to give a fair description of the product and its capabilities. As the information contained herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by law. In practice, the substrate and environmental conditions vary widely, making it essential for the user to determine the product's suitability for a particular application and that the product is not used beyond its physical limitations. The user is responsible for checking the suitability of products for their intended use.

***NOTE**

Field service where provided does not constitute supervisory responsibility. Suggestions made by Waterproofing Products Australia either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Waterproofing Products Australia, are responsible for carrying out procedures appropriate to a specific application.

DOCUMENT CONTROL	
Product	WPA 560
Initial Issue	August 2013
Technical Amendment	July 2016
	September 2020
Author	FM

Technical Data Sheets are subject to change without notice. For latest revision, check our website at www.wpa-aus.com.au

This is a CONTROLLED document under WPA's Quality System.